



## RP-20 X 100 SPECIFICATIONS

CONSTRUCTION	HDPE 900 Denier $\pm$ 10% (clear) 5x4 counts per inch in warp & fill
COATING	1½ Mils each ( $\pm$ ¼ Mils)
COLOR	Clear
WIDTH	20 ft. $\pm$ 1 in.
PUT UP	100 ft. $\pm$ 1 ft.
WEIGHT	3.13 oz/yd <sup>2</sup> (ASTM D-1910)
TOTAL THICKNESS	6½ Mils $\pm$ ¼ Mils (ASTM D-2103)
TENSILE STRENGTH	79.0 lbs. Warp 76.0 lbs Fill (ASTM D-1682, grab)
TEAR STRENGTH	6400 Grams Warp 6400 Grams Fill (ADTM D-1424 elemendorf)
BURSTING STRENGTH	129.0 P.S.I. (ASTM d-751 Mullen)
HYDROSTATIC RESISTANCE	40.4 P.S.I. (ASTM D-751)

To the best of our knowledge, the information contained herein is accurate. The information provided is based upon data furnished by our suppliers. However, *Mauritzon Inc.* assumes no liability whatsoever for the accuracy or completeness of the information contained herein. While believed to be reliable, the information of products are intended for use by skilled persons at their own risk. Final determination of suitability of any material is the sole responsibility of the user. All materials may present unknown hazards and should be used with caution. Although certain hazards are described herein, we cannot guarantee that these are the only hazards that exist.

